Nazdar 60015820CV UV Tamper Proof Clear



The 60015820CV UV Tamper Proof Clear is to be printed on polycarbonate labels used in security applications. Labels are generally printed sub-surface on transparent film. In the event of tampering or attempts to remove the label, labels printed with this clear will be destroyed.

Specific Use

Print 60015820CV Tamper-Proof Clear in a graphic pattern (such as the word "void") in the graphic area.

Use 3400 Series inks for graphic printing. 3400 inks (with 5% NB80 Adhesion Promoter) may be printed over HP Indigo digital offset prints. Refer to the 3400 Series Technical Data Sheet for processing information.

Possible label constructions are the following:

- UV Tamper Proof Clear, 3400 ink, laminating adhesive
- 3400 inks, UV Tamper Proof Clear, 3400 inks, laminating adhesive
- HP Indigo digital offset print, UV Tamper Proof Clear, 3400 white with 5% NB80 Adhesion Promoter as background, laminating adhesive

The printer is responsible for testing print and ink combinations for satisfactory performance in the end use environment for a particular label.

Substrates

Polycarbonate (PC)

Substrate recommendations are based on commonly available materials intended for the ink's specific market when the inks are processed according to this technical data. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Reference the 'Quality Statement' at the end of this document.

Mesh

305-380 tpi (120-150 tpcm) monofilament polyester mesh for most applications.

Stencil

Use direct emulsions and capillary films which are solvent resistant and UV compatible.

Squeegee

70-80 durometer polyurethane squeegee.

Coverage

Depending upon ink deposit, the estimated coverage per gallon: 2,000 – 3,500 square feet (185 - 325 square meters) Reference www.nazdar.com/en-us/ColorStar for examples of coverage calculations.

Screen Printing

Standard items are formulated to be press ready. Thoroughly mix the ink prior to printing. Improper mixing can lead to inconsistent color and ink performance.

Maintain ink temperature at 65°-90°F (18°-32°C) for optimum print and cure performance. Lower temperatures increase the ink viscosity, impairing flow and increasing film thickness. Elevated temperatures lower the ink viscosity, reducing print definition and film thickness.

Pretest to determine optimum printing parameters for a particular set of ink, substrate, screen, press, and curing variables/conditions.

The ink can be affected by stray UV light. Be aware of skylights, windows and overhead lights curing the ink in the screen; light filters are recommended. Leaving a container uncovered may result in the ink's surface forming a "skin", caused by reaction with ambient lighting. Keep containers covered.

Nazdar does not recommend inter-mixing this ink series with other inks or series.

 Revision date
 Nov-21-2023
 Revision 5

 © Nazdar Ink Technologies
 . www.nazdar.com
 . nazdarorders@nazdar.com
 . TechSupport@nazdar.com

Nazdar 60015820CV UV Tamper Proof Clear



Cure Parameters

These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions. "Undercuring" the ink may result in poor adhesion, lower block resistance, reduced durability, and higher residual odor. "Overcuring" the ink may reduce the flexibility of the printed part and adhesion of subsequent ink layers.

Mercury Vapor UV Curing: this series has been optimized for 395nm LED curing; however, most colors cure when exposed to a single medium pressure mercury vapor lamp emitting output millijoules (mJ) and milliwatts (mW) of:

150+ mJ/cm² @ 600+ mW/cm² UVA

These guidelines are representative of measurements taken using an EIT® UVICURE® Plus radiometer measuring the UVA bandwidth (320-390 nm). To obtain accurate mJ readings with the UVICURE® Plus, reduce the belt speed to less than 40 ft/min.

Adhesion Testing

When recommended UV energy output levels are achieved, checking the degree of cure on a cooled down print is imperative:

- Touch of ink surface the ink surface should be smooth.
- Thumb twist the ink surface should not mar or smudge.

Cleanup

For screen cleaning, similar products to those listed below may be used.

Screen Wash (Prior to Reclaim): Use IMS201 Premium Graphic Screen Wash or IMS203 Economy Graphic Screen Wash Press Wash (On Press): Use IMS301 Premium Graphic Press Wash

Ink Modifications

Additives

The market specific performance properties of this ink series / ink item should be acceptable for most applications without the need for additives. When required, any additives should be thoroughly mixed before each use. Prior to production, test any additive adjustment to the ink. Inks containing additives should not be mixed with other inks.

Prior to production, test any additive adjustment to the ink. Inks containing additives should not be mixed with other inks.

Example for additives: Ink at 100g with 8% of an additive is calculated as: 100g ink + 8g additive = 108g total

Retarder

Use <u>RE306 Reducer</u> to reduce the viscosity of the ink. Add up to 10%. Over reduction can reduce film thickness and adversely affect cure.

General Information

Handling

Refer to the SDS for recommendations on handling.

© Nazdar Ink Technologies

Wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If product does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water.

Consult the applicable Safety Data Sheet (SDS / MSDS) for further instructions and warnings.

www.nazdar.com

For assistance on a wide range of important regulatory issues, consult the following Regulatory Compliance Department link at http://www.nazdar.com or contact Nazdar Ink Technologies - World Headquarters (see contact listing at the end of this document).

This ink series is a one-part, 100% solids UV-curable screen printing ink and does not contain N-vinyl-2-pyrrolidone (trade name V-Pyrol®).

Storage / Shelf Life

Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life.

Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink. Store

Revision date Nov-21-2023 Revision 5

nazdarorders@nazdar.com

TechSupport@nazdar.com

Nazdar 60015820CV UV Tamper Proof Clear



closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life.

Standard items supplied in 1-gallon (4/5 kilo) containers or smaller. Useable for a period of at least **12 months** from the date of manufacture.

Shelf life above applies to the standard ink items listed on this TDS. To obtain the shelf life for special inks and additives, contact Nazdar Customer Service or Nazdar Technical Service. See contact listing at the end of this document.

Standard Color Range

Based on information from our raw material suppliers, these ink products are formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

Packaging / Availability

Contact your Nazdar distributor for product availability and offering.

Item Type	Item Number	Item (or Color) Description
Clears / Varnishes	60015820CV	UV Tamper Proof Clear
Additives	RE306	Reducer
Cleaners	IMS201	Premium Graphic Screen Wash
Cleaners	IMS203	Economy Graphic Screen Wash
Cleaners	IMS301	Premium Graphic Press Wash

Nazdar Quality Statement

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

Nazdar Ink Technologies Offices

Nazdar Ink Technologies - World Headquarters

8501 Hedge Lane Terrace Shawnee, KS 66227-3290 USA Toll Free US: 866-340-3579

Tel: +1 913-422-2255 Fax: +1 913-422-2296

Customer Service E-mail: NazdarOrders@nazdar.com Technical Support E-mail: TechSupport@Nazdar.com

Nazdar Limited – EMEA Battersea Road, Heaton Mersey Stockport, England SK4 3EA Tel: + 44 (0)-161-442-2111 Fax: + 44 (0)-161-442-2001

EMEA Customer Service E-mail: infoUK@nazdar.com

EMEA Technical Service E-mail: technicalservicesUK@nazdar.com

Nazdar – Asia Pacific 11 Changi North Street 1 #03-03/04 Singapore 498823

Tel: +65 6385 4611 E-mail: aspac@nazdar.com

Revision date Nov-21-2023 Revision 5